

YG YG-1 CO., LTD.

HEAD OFFICE

211, Sewolcheon-ro, Bupyeong-gu, Incheon, South Korea

Phone: +82-32-526-0909

Http://www.yg1.kr

E-mail: yg1@yg1.kr

Note The information is provided for reference only. Tool specifications are subject to change without prior notice.
Although we endeavor to supply accurate and timely information, there can be no guarantee to cover every particular application.
YG-1 or publishers are not liable for any damage for use of the information.

 **YouTube**    
Search 'YG-1' on social media outlets

YG1YEP190826004



PRODUCT FEATURES



- Chatter and Harmonics Reduced for **Improved Stability and Better Finishing**
- Special Design of Flute Geometry for **Optimal Chip Formation and Chip Evacuation**
- Engineered Coating Technology to **Reduced Wear and Increase Heat Resistance**
- Enhanced Corner Geometry for **Longer Tool Life**

PRODUCT GEOMETRY




V7 PLUS 6 FLUTE END MILLS



THE BEST CHATTER FREE TOOL FOR HIGH SPEED


- Unique geometry of the variable pitch provides the best chatter free tool for high speed and also trochoidal milling
- Several slot widths can be used with the same tool diameter in an efficient way
- Provides longer tool life and higher productivity on most materials
- Trochoidal milling is a programming technique applying a small radial width of cut with also higher cutting speed and feed per tooth

Trochoidal Milling performs better than conventional ways because it has..



- Lower Cutting Force from smaller arc engagement
- Longer Tool Life from more flutes, and deeper cutting depth
- Higher Stability, Lower Vibration and Excellent Chip Evacuation

V7 PLUS 6 FLUTE CHIP SPLITTER **NEW**




GUIDE LINE TO ICONS

Tool Raw Material



Helix Angle



No. of Flutes



Tolerance of Ball Radius



Type of Shank



Chamfer Angle






Cutting Condition Pages



CASE STUDY


V7 Plus 4 Flute vs Competitor

	V7 Plus	Competitor
Wear(μm)	83.518	203.381
Milling Length(m)	49	49
Size(mm)	Ø10 x Ø10 x 22 x 72	
Work Material	-DIN: C45 -WR: 1.0503 -JIS: S45C (HRC 30 / HB 286)	
Cutting Speed	230.09 m/min.	
RPM	7,324 rev./min.	
Feed	1,464 mm/min.	
Feed per tooth	0.05 mm/tooth	
Milling Method	Down & Side Cutting	
Milling Depth	Axial: 10 mm, Radial: 3 mm	
Coolant	Wet Cut	
Overhang	34 mm	
Machine	Machining Center	



V7 Plus 4 Flute vs Competitor




	V7 Plus	Competitor
Wear(μm)	81.485	183.296
Milling Length(m)	58.8	58.8
Size(mm)	Ø16 x Ø16 x 32 x 92	
Work Material	-DIN: C45 -WR: 1.0503 -JIS: S45C (HRC 30 / HB 286)	
Cutting Speed	160.00 m/min.	
RPM	3,183 rev./min.	
Feed	573 mm/min.	
Feed per tooth	0.05 mm/tooth	
Milling Method	Down & Side Cutting	
Milling Depth	Axial: 14 mm, Radial: 3 mm	
Coolant	Wet Cut	
Overhang	45 mm	
Machine	Machining Center	



CASE STUDY



V7 Plus 6 Flute Chip Splitter vs Competitor

	V7 Plus	Competitor
Wear(μm)	32.49	88.26
Milling Length(m)	310	155
Size(mm)	Ø12 x Ø12 x 48 x 120 with chip Splitter	
Work Material	-DIN: C45 -WR: 1.0503 -JIS: S45C (HRC 30 / HB 286)	
Cutting Speed	220.01 m/min.	
RPM	5,836 rev./min.	
Feed	3,151 mm/min.	
Milling Method	Trochoidal Cutting	
Milling Depth	Axial: 36mm, Radial: 0.6 mm	
Coolant	Wet Cut	
Overhang	56 mm	
Machine	Machining Center	



V7 Plus 6 Flute vs Competitor

	V7 Plus	Competitor
Milling Length(m)	360	300
Size(mm)	Ø12(R1) x Ø12 x 26 x 83	
Work Material	-DIN: C45 -WR: 1.0503 -JIS: S45C (HRC 30 / HB 286)	
Cutting Speed	278.67 m/min.	
RPM	7,392 rev./min.	
Feed	7,495 mm/min.	
Feed per tooth	0.17 mm/tooth	
Milling Method	Trochoidal Cutting	
Milling Depth	Axial: 24 mm(2D), Radial: 0.6 mm(0.05D)	
Coolant	Wet Cut	
Overhang	36 mm	
Machine	Machining Center	



SELECTION GUIDE





HIGH PERFORMANCE
SOLID CARBIDE END MILLS
For Steels, Cast Iron and Stainless Steels

◎ : Excellent ○ : Good										
ISO	VDI 3323	Material Description	Composition / Structure / Heat Treatment		HB	HRc				
P	1	Non-alloy steel	About 0.15% C	Annealed	125		◎	◎	◎	◎
	2		About 0.45% C	Annealed	190	13	◎	◎	◎	◎
	3		About 0.45% C	Quenched & tempered	250	25	◎	◎	◎	◎
	4		About 0.75% C	Annealed	270	28	◎	◎	◎	◎
	5		About 0.75% C	Quenched & tempered	300	32	◎	◎	◎	◎
	6	Low alloy steel		Annealed	180	10	◎	◎	◎	◎
	7			Quenched & tempered	275	29	◎	◎	◎	◎
	8			Quenched & tempered	300	32	◎	◎	◎	◎
	9			Quenched & tempered	350	38	◎	◎	◎	◎
	10	High alloyed steel, and tool steel		Annealed	200	15	◎	◎	◎	◎
	11			Quenched & Tempered	325	35	◎	◎	◎	◎
M	12	Stainless steel	Ferritic / Martensitic	Annealed	200	15	◎	◎	◎	◎
	13		Martensitic	Quenched & Tempered	240	23	◎	◎	◎	◎
	14			Austenitic	180	10	◎	◎	◎	◎
K	15	Grey cast iron	Pearlitic / ferritic		180	10	◎	◎	◎	◎
	16		Pearlitic (Martensitic)		260	26	◎	◎	◎	◎
	17	Nodular cast iron	Ferritic		160	3	◎	◎	◎	◎
	18		Pearlitic		250	25	◎	◎	◎	◎
	19	Malleable cast iron	Ferritic		130		◎	◎	◎	◎
	20		Pearlitic		230	21	◎	◎	◎	◎
N	21	Aluminum-wrought alloy	Not Curable		60					
	22		Curable Hardened		100					
	23	Aluminum-cast, alloyed	≤ 12% Si, Not Curable		75					
	24		≤ 12% Si, Curable Hardened		90					
	25		> 12% Si, Not Curable		130					
	26	Copper and Copper Alloys (Bronze / Brass)	Cutting Alloys, PB>1%		110					
	27		CuZn, CuSnZn (Brass)		90					
	28		CuSn, lead-free copper and electrolytic copper		100					
	29	Non Metallic Materials	Duroplastic, Fiber Reinforced Plastic							
	30		Rubber, Wood, etc.							
S	31	Heat Resistant Super Alloys	Fe Based	Annealed	200	15	○	○	○	○
	32			Cured	280	30	○	○	○	○
	33			Annealed	250	25	○	○	○	○
	34		Ni or Co Based	Cured	350	38	○	○	○	○
	35			Cast	320	34	○	○	○	○
	36	Titanium Alloys	Pure Titanium		400 Rm		○	○	○	○
	37		Alpha + Beta Alloys	Hardened	1050 Rm		○	○	○	○
H	38	Hardened steel		Hardened	550	55				
	39			Hardened	630	60				
	40	Chilled Cast Iron		Cast	400	42				
	41	Hardened Cast Iron		Hardened	550	55				

HIGH PERFORMANCE SOLID CARBIDE END MILLS
4 FLUTE BALL NOSE

GMG55 PLAIN SHANK
GMG56 FLAT SHANK

- Special flute geometry and multiple helix eliminate vibrations
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



EDP No.		Radius of Ball Nose	Mill Diameter	Shank Diameter	Length of Cut		Overall Length
PLAIN	FLAT	R (±0.02)	D1	D2	L1	L2	
GMG55030	GMG56030	R1.5	3.0	6	8	57	
GMG55040	GMG56040	R2.0	4.0	6	11	57	
GMG55050	GMG56050	R2.5	5.0	6	13	57	
GMG55060	GMG56060	R3.0	6.0	6	13	57	
GMG55080	GMG56080	R4.0	8.0	8	19	63	
GMG55100	GMG56100	R5.0	10.0	10	22	72	
GMG55120	GMG56120	R6.0	12.0	12	26	83	
GMG55160	GMG56160	R8.0	16.0	16	32	92	
GMG55200	GMG56200	R10.0	20.0	20	38	104	
GMG55250	GMG56250	R12.5	25.0	25	38	104	

Unit : mm


Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5 * Shank Dia. ≥ Ø12: h6
Over Ø12	0 ~ - 0.03	

◎ : Excellent ○ : Good																					
ISO	P										M				K						
Material Description	Non-alloy steel					Low alloy steel				High alloyed steel, and tool steel		Stainless steel				Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	
HRC		13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25		21	
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230	
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	
ISO	N										S						H				
Material Description	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)			Non Metallic Materials		Heat Resistant Super Alloys				Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron		
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRC											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommended											○	○	○	○	○	○	○				

HIGH PERFORMANCE SOLID CARBIDE END MILLS
4 FLUTE CORNER RADIUS SHORT LENGTH

GMF54 PLAIN SHANK
GMF55 FLAT SHANK

- Special flute geometry and multiple helix eliminate vibrations
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut		Overall Length
PLAIN	FLAT	R	D1	D2	L1	L2	
GMF54030	GMF55030	R0.3	3.0	6	7	54	
GMF54901	GMF55901	R0.5	3.0	6	7	54	
GMF54040	GMF55040	R0.3	4.0	6	8	54	
GMF54902	GMF55902	R0.5	4.0	6	8	54	
GMF54050	GMF55050	R0.3	5.0	6	10	54	
GMF54903	GMF55903	R0.5	5.0	6	10	54	
GMF54060	GMF55060	R0.3	6.0	6	10	54	
GMF54904	GMF55904	R0.5	6.0	6	10	54	
GMF54905	GMF55905	R1.0	6.0	6	10	54	
GMF54080	GMF55080	R0.5	8.0	8	12	58	
GMF54906	GMF55906	R1.0	8.0	8	12	58	
GMF54100	GMF55100	R0.5	10.0	10	14	66	
GMF54907	GMF55907	R1.0	10.0	10	14	66	
GMF54120	GMF55120	R0.5	12.0	12	16	73	
GMF54908	GMF55908	R1.0	12.0	12	16	73	
GMF54909	GMF55909	R2.0	12.0	12	16	73	
GMF54140	GMF55140	R0.5	14.0	14	18	75	
GMF54160	GMF55160	R1.0	16.0	16	22	82	
GMF54912	GMF55912	R2.0	16.0	16	22	82	
GMF54913	GMF55913	R3.0	16.0	16	22	82	
GMF54180	GMF55180	R1.0	18.0	18	24	84	
GMF54200	GMF55200	R1.0	20.0	20	26	92	
GMF54916	GMF55916	R2.0	20.0	20	26	92	
GMF54917	GMF55917	R3.0	20.0	20	26	92	

Unit : mm


Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5 * Shank Dia. ≥ Ø12: h6
Over Ø12	0 ~ - 0.03	

◎ : Excellent ○ : Good																							
ISO	P										M				K								
Material Description	Non-alloy steel					Low alloy steel				High alloyed steel, and tool steel		Stainless steel			Grey cast iron		Nodular cast iron		Malleable cast iron				
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20			
Hfrc		13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25		21			
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230			
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎			
ISO	N										S					H							
Material Description	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze/ Brass)			Non Metallic Materials		Heat Resistant Super Alloys					Titanium Alloys		Hardened steel		Chilled Cast Iron		Hardened Cast Iron	
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41		
Hfrc											15	30	25	38	34			55	60	42	55		
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550		
Recommended											○	○	○	○	○	○	○						

HIGH PERFORMANCE SOLID CARBIDE END MILLS 4 FLUTE CORNER RADIUS LONG LENGTH

GMF58 PLAIN SHANK
GMF59 FLAT SHANK

- Special flute geometry and multiple helix eliminate vibrations
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	R	D1	D2	L1	L2
GMF58030	GMF59030	R0.3	3.0	6	8	57
GMF58901	GMF59901	R0.5	3.0	6	8	57
GMF58040	GMF59040	R0.3	4.0	6	11	57
GMF58902	GMF59902	R0.5	4.0	6	11	57
GMF58050	GMF59050	R0.3	5.0	6	13	57
GMF58903	GMF59903	R0.5	5.0	6	13	57
GMF58060	GMF59060	R0.3	6.0	6	13	57
GMF58904	GMF59904	R0.5	6.0	6	13	57
GMF58905	GMF59905	R1.0	6.0	6	13	57
GMF58080	GMF59080	R0.5	8.0	8	19	63
GMF58906	GMF59906	R1.0	8.0	8	19	63
GMF58100	GMF59100	R0.5	10.0	10	22	72
GMF58907	GMF59907	R1.0	10.0	10	22	72
GMF58120	GMF59120	R0.5	12.0	12	26	83
GMF58908	GMF59908	R1.0	12.0	12	26	83
GMF58909	GMF59909	R2.0	12.0	12	26	83
GMF58140	GMF59140	R0.5	14.0	14	26	83
GMF58160	GMF59160	R1.0	16.0	16	32	92
GMF58912	GMF59912	R2.0	16.0	16	32	92
GMF58913	GMF59913	R3.0	16.0	16	32	92
GMF58180	GMF59180	R1.0	18.0	18	32	92
GMF58200	GMF59200	R1.0	20.0	20	38	104
GMF58916	GMF59916	R2.0	20.0	20	38	104
GMF58917	GMF59917	R3.0	20.0	20	38	104
GMF58250	GMF59250	R1.0	25.0	25	38	104

Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5 * Shank Dia. ≥ Ø12: h6
Over Ø12	0 ~ - 0.03	


◎ : Excellent ○ : Good

ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel				Stainless steel			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	38	10	29	32	38	15	35	15	23	10	10	26	3	25
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
ISO	N										S				H			
Material Description	Aluminum-wrought alloy					Aluminum-cast, alloyed					Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	40	42	55
HB						200	280	250	350	320	400 Rm	1050 Rm	550	630	400	400	550	550
Recommended						○	○	○	○	○	○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 4 FLUTE CORNER RADIUS WITH NECK

GMF62 PLAIN SHANK
GMF63 FLAT SHANK

- Special flute geometry and multiple helix eliminate vibrations
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
PLAIN	FLAT	R	D1	D2	L1	L3	L2	D3
GMF62030	GMF63030	R0.3	3.0	6	7	12	54	2.7
GMF62901	GMF63901	R0.5	3.0	6	7	12	54	2.7
GMF62902	GMF63902	R0.3	3.0	6	7	17	57	2.7
GMF62903	GMF63903	R0.5	3.0	6	7	17	57	2.7
GMF62040	GMF63040	R0.3	4.0	6	8	15	57	3.7
GMF62904	GMF63904	R0.5	4.0	6	8	15	57	3.7
GMF62905	GMF63905	R0.3	4.0	6	8	22	63	3.7
GMF62906	GMF63906	R0.5	4.0	6	8	22	63	3.7
GMF62050	GMF63050	R0.3	5.0	6	10	17	57	4.7
GMF62907	GMF63907	R0.5	5.0	6	10	17	57	4.7
GMF62908	GMF63908	R0.3	5.0	6	10	27	67	4.7
GMF62909	GMF63909	R0.5	5.0	6	10	27	67	4.7
GMF62060	GMF63060	R0.3	6.0	6	10	15	57	5.5
GMF62910	GMF63910	R0.5	6.0	6	10	15	57	5.5
GMF62911	GMF63911	R1.0	6.0	6	10	15	57	5.5
GMF62912	GMF63912	R0.3	6.0	6	10	20	62	5.5
GMF62913	GMF63913	R0.5	6.0	6	10	20	62	5.5
GMF62914	GMF63914	R1.0	6.0	6	10	20	62	5.5
GMF62915	GMF63915	R0.3	6.0	6	10	32	74	5.5
GMF62916	GMF63916	R0.5	6.0	6	10	32	74	5.5
GMF62917	GMF63917	R1.0	6.0	6	10	32	74	5.5
GMF62080	GMF63080	R0.5	8.0	8	12	20	63	7.5
GMF62918	GMF63918	R1.0	8.0	8	12	20	63	7.5
GMF62919	GMF63919	R0.5	8.0	8	12	30	73	7.5

Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5 * Shank Dia. ≥ Ø12: h6
Over Ø12	0 ~ - 0.03	


◎ : Excellent ○ : Good

ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel				Stainless steel			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	38	10	29	32	38	15	35	15	23	10	10	26	3	25
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
ISO	N										S				H			
Material Description	Aluminum-wrought alloy					Aluminum-cast, alloyed					Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	40	42	55
HB						200	280	250	350	320	400 Rm	1050 Rm	550	630	400	400	550	550
Recommended						○	○	○	○	○	○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 4 FLUTE CORNER RADIUS WITH NECK

GMF62 PLAIN SHANK
GMF63 FLAT SHANK

- Special flute geometry and multiple helix eliminate vibrations
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
PLAIN	FLAT	R	D1	D2	L1	L3	L2	D3
GMF62920	GMF63920	R1.0	8.0	8	12	30	73	7.5
GMF62921	GMF63921	R0.5	8.0	8	12	46	90	7.5
GMF62922	GMF63922	R1.0	8.0	8	12	46	90	7.5
GMF62100	GMF63100	R0.5	10.0	10	14	25	72	9.2
GMF62923	GMF63923	R1.0	10.0	10	14	25	72	9.2
GMF62924	GMF63924	R0.5	10.0	10	14	35	82	9.2
GMF62925	GMF63925	R1.0	10.0	10	14	35	82	9.2
GMF62926	GMF63926	R0.5	10.0	10	14	55	102	9.2
GMF62927	GMF63927	R1.0	10.0	10	14	55	102	9.2
GMF62120	GMF63120	R0.5	12.0	12	16	30	83	11.0
GMF62928	GMF63928	R1.0	12.0	12	16	30	83	11.0
GMF62929	GMF63929	R2.0	12.0	12	16	30	83	11.0
GMF62930	GMF63930	R0.5	12.0	12	16	40	93	11.0
GMF62931	GMF63931	R1.0	12.0	12	16	40	93	11.0
GMF62932	GMF63932	R2.0	12.0	12	16	40	93	11.0
GMF62933	GMF63933	R0.5	12.0	12	16	64	117	11.0
GMF62934	GMF63934	R1.0	12.0	12	16	64	117	11.0
GMF62935	GMF63935	R2.0	12.0	12	16	64	117	11.0
GMF62160	GMF63160	R1.0	16.0	16	22	38	92	15.0
GMF62936	GMF63936	R2.0	16.0	16	22	38	92	15.0
GMF62937	GMF63937	R3.0	16.0	16	22	38	92	15.0
GMF62938	GMF63938	R1.0	16.0	16	22	55	109	15.0
GMF62939	GMF63939	R2.0	16.0	16	22	55	109	15.0
GMF62940	GMF63940	R3.0	16.0	16	22	55	109	15.0

► NEXT PAGE

Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5 * Shank Dia. ≥ Ø12: h6
Over Ø12	0 ~ - 0.03	

◎ : Excellent ○ : Good


ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloy steel, and tool steel				Stainless steel			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

ISO	N										S				H			
Material Description	Aluminum-wrought alloy					Aluminum-cast, alloyed					Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	40	40	55
HB						200	280	250	350	320	400 Rm	1050 Rm	550	630	400	400	400	550
Recommended						○	○	○	○	○	○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 4 FLUTE CORNER RADIUS WITH NECK

GMF62 PLAIN SHANK
GMF63 FLAT SHANK

- Special flute geometry and multiple helix eliminate vibrations
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter
PLAIN	FLAT	R	D1	D2	L1	L3	L2	D3
GMF62941	GMF63941	R1.0	16.0	16	22	87	141	15.0
GMF62942	GMF63942	R2.0	16.0	16	22	87	141	15.0
GMF62943	GMF63943	R3.0	16.0	16	22	87	141	15.0
GMF62200	GMF63200	R1.0	20.0	20	26	50	104	19.0
GMF62944	GMF63944	R2.0	20.0	20	26	50	104	19.0
GMF62945	GMF63945	R3.0	20.0	20	26	50	104	19.0
GMF62946	GMF63946	R1.0	20.0	20	26	70	124	19.0
GMF62947	GMF63947	R2.0	20.0	20	26	70	124	19.0
GMF62948	GMF63948	R3.0	20.0	20	26	70	124	19.0
GMF62949	GMF63949	R1.0	20.0	20	26	110	164	19.0
GMF62950	GMF63950	R2.0	20.0	20	26	110	164	19.0
GMF62951	GMF63951	R3.0	20.0	20	26	110	164	19.0

Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5 * Shank Dia. ≥ Ø12: h6
Over Ø12	0 ~ - 0.03	

◎ : Excellent ○ : Good


ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloy steel, and tool steel				Stainless steel			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	30	10	29	32	38	15	35	15	23	10	10	26	3	25
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

ISO	N										S				H			
Material Description	Aluminum-wrought alloy					Aluminum-cast, alloyed					Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	40	40	55
HB						200	280	250	350	320	400 Rm	1050 Rm	550	630	400	400	400	550
Recommended						○	○	○	○	○	○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 4 FLUTE with EXTENDED NECK

GMF60 PLAIN SHANK GMF61 FLAT SHANK


- Special flute geometry and multiple helix eliminate vibrations
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Chamfer
PLAIN	FLAT	D1	D2	L1	L3	L2	D3	
GMF60030	GMF61030	3.0	6	7	12	54	2.7	0.10
GMF60901	GMF61901	3.0	6	7	17	57	2.7	0.10
GMF60902	GMF61902	3.0	6	8	14	57	2.7	0.10
GMF60040	GMF61040	4.0	6	8	15	57	3.7	0.15
GMF60903	GMF61903	4.0	6	8	22	63	3.7	0.15
GMF60904	GMF61904	4.0	6	11	16	57	3.7	0.15
GMF60050	GMF61050	5.0	6	10	17	57	4.7	0.15
GMF60905	GMF61905	5.0	6	10	27	67	4.7	0.15
GMF60906	GMF61906	5.0	6	13	18	57	4.7	0.15
GMF60060	GMF61060	6.0	6	10	15	57	5.5	0.20
GMF60907	GMF61907	6.0	6	10	20	62	5.5	0.20
GMF60908	GMF61908	6.0	6	10	32	74	5.5	0.20
GMF60909	GMF61909	6.0	6	13	21	57	5.5	0.20
GMF60080	GMF61080	8.0	8	12	20	63	7.5	0.20
GMF60910	GMF61910	8.0	8	12	30	73	7.5	0.20
GMF60911	GMF61911	8.0	8	12	46	90	7.5	0.20
GMF60912	GMF61912	8.0	8	19	27	63	7.5	0.20
GMF60100	GMF61100	10.0	10	14	25	72	9.2	0.30
GMF60913	GMF61913	10.0	10	14	35	82	9.2	0.30
GMF60914	GMF61914	10.0	10	14	55	102	9.2	0.30
GMF60915	GMF61915	10.0	10	22	32	72	9.2	0.30

Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5
Over Ø12	0 ~ - 0.03	* Shank Dia. ≥ Ø12: h6



Enforced Cutting Edge

◎ : Excellent ○ : Good


ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloy steel, and tool steel				Stainless steel			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	35	10	29	32	38	15	35	15	23	10	10	26	3	25
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

ISO	N										S				H			
Material Description	Aluminum-wrought alloy					Aluminum-cast, alloyed					Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	40	40	55
HB						200	280	250	350	320	400 Rm	1050 Rm						550
Recommended						○	○	○	○	○	○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 4 FLUTE with EXTENDED NECK

GMF60 PLAIN SHANK GMF61 FLAT SHANK


- Special flute geometry and multiple helix eliminate vibrations
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Length Below Shank	Overall Length	Neck Diameter	Chamfer
PLAIN	FLAT	D1	D2	L1	L3	L2	D3	
GMF60120	GMF61120	12.0	12	16	30	83	11.0	0.35
GMF60916	GMF61916	12.0	12	16	40	93	11.0	0.35
GMF60917	GMF61917	12.0	12	16	64	117	11.0	0.35
GMF60918	GMF61918	12.0	12	26	38	83	11.0	0.35
GMF60160	GMF61160	16.0	16	22	38	92	15.0	0.40
GMF60919	GMF61919	16.0	16	22	55	109	15.0	0.40
GMF60920	GMF61920	16.0	16	22	87	141	15.0	0.40
GMF60921	GMF61921	16.0	16	32	44	92	15.0	0.40
GMF60200	GMF61200	20.0	20	26	50	104	19.0	0.50
GMF60922	GMF61922	20.0	20	26	70	124	19.0	0.50
GMF60923	GMF61923	20.0	20	26	110	164	19.0	0.50
GMF60924	GMF61924	20.0	20	38	54	104	19.0	0.50

Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5
Over Ø12	0 ~ - 0.03	* Shank Dia. ≥ Ø12: h6



Enforced Cutting Edge

◎ : Excellent ○ : Good


ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloy steel, and tool steel				Stainless steel			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	35	10	29	32	38	15	35	15	23	10	10	26	3	25
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎

ISO	N										S				H			
Material Description	Aluminum-wrought alloy					Aluminum-cast, alloyed					Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	40	40	55
HB						200	280	250	350	320	400 Rm	1050 Rm						550
Recommended						○	○	○	○	○	○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 6 FLUTE CORNER RADIUS LONG LENGTH

GMG16 PLAIN SHANK
GMG17 FLAT SHANK

- The unique geometry of the variable pitch provides the best chatter free tool for high speed and trochoidal milling
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	R	D1	D2	L1	L2
GMG16060	GMG17060	R0.5	6.0	6	13	57
GMG16901	GMG17901	R1.0	6.0	6	13	57
GMG16080	GMG17080	R0.5	8.0	8	19	63
GMG16902	GMG17902	R1.0	8.0	8	19	63
GMG16100	GMG17100	R0.5	10.0	10	22	72
GMG16903	GMG17903	R1.0	10.0	10	22	72
GMG16904	GMG17904	R1.5	10.0	10	22	72
GMG16905	GMG17905	R2.0	10.0	10	22	72
GMG16120	GMG17120	R0.5	12.0	12	26	83
GMG16906	GMG17906	R1.0	12.0	12	26	83
GMG16907	GMG17907	R1.5	12.0	12	26	83
GMG16908	GMG17908	R2.0	12.0	12	26	83
GMG16909	GMG17909	R3.0	12.0	12	26	83
GMG16160	GMG17160	R1.0	16.0	16	32	92
GMG16910	GMG17910	R1.5	16.0	16	32	92
GMG16911	GMG17911	R2.0	16.0	16	32	92
GMG16912	GMG17912	R3.0	16.0	16	32	92
GMG16200	GMG17200	R1.0	20.0	20	38	104
GMG16913	GMG17913	R1.5	20.0	20	38	104
GMG16914	GMG17914	R2.0	20.0	20	38	104
GMG16915	GMG17915	R3.0	20.0	20	38	104
GMG16250	GMG17250	R1.0	25.0	25	44	104
GMG16916	GMG17916	R1.5	25.0	25	44	104
GMG16917	GMG17917	R2.0	25.0	25	44	104
GMG16918	GMG17918	R3.0	25.0	25	44	104

Mill Dia. Tolerance (mm)		Shank Dia. Tolerance
Up to Ø12	0 ~ - 0.02	h5 * Shank Dia. ≥ Ø12: h6
Over Ø12	0 ~ - 0.03	


◎ : Excellent ○ : Good

ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel				Stainless steel			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	38	10	29	32	38	15	35	15	23	10	10	26	3	25
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
ISO	N										S				H			
Material Description	Aluminum-wrought alloy					Aluminum-cast, alloyed					Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	40	42	55
HB						200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550		
Recommended						○	○	○	○	○	○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 6 FLUTE CORNER RADIUS EXTRA LONG LENGTH

GMG18 PLAIN SHANK
GMG19 FLAT SHANK

- The unique geometry of the variable pitch provides the best chatter free tool for high speed and trochoidal milling
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	R	D1	D2	L1	L2
GMG18060	GMG19060	R0.5	6.0	6	24	75
GMG18901	GMG19901	R1.0	6.0	6	24	75
GMG18080	GMG19080	R0.5	8.0	8	32	75
GMG18902	GMG19902	R1.0	8.0	8	32	75
GMG18903	GMG19903	R2.0	8.0	8	32	75
GMG18100	GMG19100	R0.5	10.0	10	40	100
GMG18904	GMG19904	R1.0	10.0	10	40	100
GMG18905	GMG19905	R1.5	10.0	10	40	100
GMG18906	GMG19906	R2.0	10.0	10	40	100
GMG18120	GMG19120	R0.5	12.0	12	48	120
GMG18907	GMG19907	R1.0	12.0	12	48	120
GMG18908	GMG19908	R1.5	12.0	12	48	120
GMG18909	GMG19909	R2.0	12.0	12	48	120
GMG18910	GMG19910	R3.0	12.0	12	48	120
GMG18160	GMG19160	R1.0	16.0	16	64	140
GMG18911	GMG19911	R1.5	16.0	16	64	140
GMG18912	GMG19912	R2.0	16.0	16	64	140
GMG18913	GMG19913	R3.0	16.0	16	64	140
GMG18200	GMG19200	R1.0	20.0	20	80	150
GMG18914	GMG19914	R1.5	20.0	20	80	150
GMG18915	GMG19915	R2.0	20.0	20	80	150
GMG18916	GMG19916	R3.0	20.0	20	80	150
GMG18917	GMG19917	R4.0	20.0	20	80	150

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5 * Shank Dia. ≥ Ø12: h6


◎ : Excellent ○ : Good

ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloyed steel, and tool steel				Stainless steel			
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	38	10	29	32	38	15	35	15	23	10	10	26	3	25
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
ISO	N										S				H			
Material Description	Aluminum-wrought alloy					Aluminum-cast, alloyed					Copper and Copper Alloys (Bronze / Brass)				Non Metallic Materials			
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	40	42	55
HB						200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550		
Recommended						○	○	○	○	○	○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 6 FLUTE CORNER RADIUS EXTRA LONG LENGTH

GMG18 PLAIN SHANK
GMG19 FLAT SHANK

- The unique geometry of the variable pitch provides the best chatter free tool for high speed and trochoidal milling
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	R	D1	D2	L1	L2
GMG18918	GMG19918	R5.0	20.0	20	80	150
GMG18250	GMG19250	R1.0	25.0	25	100	170
GMG18919	GMG19919	R1.5	25.0	25	100	170
GMG18920	GMG19920	R2.0	25.0	25	100	170
GMG18921	GMG19921	R3.0	25.0	25	100	170
GMG18922	GMG19922	R4.0	25.0	25	100	170
GMG18923	GMG19923	R5.0	25.0	25	100	170

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5 * Shank Dia. ≥ Ø12: h6


HIGH PERFORMANCE SOLID CARBIDE END MILLS 6 FLUTE CORNER RADIUS EXTRA LONG LENGTH CHIP SPLITTER

NEW

GMH58 PLAIN SHANK
GMH59 FLAT SHANK

Launching Jan of 2020

- Special chip splitter design for better chip removal shortened chip length at high axial machining
- High Performance for Steels, Stainless Steels and Cast Iron



Unit : mm

EDP No.		Corner Radius	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	R	D1	D2	L1	L2
GMH58060	GMH59060	R0.5	6.0	6	24	75
GMH58901	GMH59901	R1.0	6.0	6	24	75
GMH58080	GMH59080	R0.5	8.0	8	32	75
GMH58902	GMH59902	R1.0	8.0	8	32	75
GMH58903	GMH59903	R2.0	8.0	8	32	75
GMH58100	GMH59100	R0.5	10.0	10	40	100
GMH58904	GMH59904	R1.0	10.0	10	40	100
GMH58905	GMH59905	R1.5	10.0	10	40	100
GMH58906	GMH59906	R2.0	10.0	10	40	100
GMH58120	GMH59120	R0.5	12.0	12	48	120
GMH58907	GMH59907	R1.0	12.0	12	48	120
GMH58908	GMH59908	R1.5	12.0	12	48	120
GMH58909	GMH59909	R2.0	12.0	12	48	120
GMH58910	GMH59910	R3.0	12.0	12	48	120
GMH58160	GMH59160	R1.0	16.0	16	64	140
GMH58911	GMH59911	R1.5	16.0	16	64	140
GMH58912	GMH59912	R2.0	16.0	16	64	140
GMH58913	GMH59913	R3.0	16.0	16	64	140
GMH58200	GMH59200	R1.0	20.0	20	80	150
GMH58914	GMH59914	R1.5	20.0	20	80	150
GMH58915	GMH59915	R2.0	20.0	20	80	150

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5 * Shank Dia. ≥ Ø12: h6

► NEXT PAGE

◎ : Excellent ○ : Good

ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloy steel, and tool steel				Stainless steel		Grey cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25	21
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
ISO	N										S				H			
Material Description	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)					Non Metallic Materials				Heat Resistant Super Alloys		Titanium Alloys	
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	55	60	42
HB											200	280	250	350	320	400 Rm	1050 Rm	550
Recommended											○	○	○	○	○	○	○	○


◎ : Excellent ○ : Good

ISO	P										M				K			
Material Description	Non-alloy steel					Low alloy steel					High alloy steel, and tool steel				Stainless steel		Grey cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18
HRC	13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25	21
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎
ISO	N										S				H			
Material Description	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)					Non Metallic Materials				Heat Resistant Super Alloys		Titanium Alloys	
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38
HRC	60	100	75	90	130	110	90	100			15	30	25	38	34	55	60	42
HB											200	280	250	350	320	400 Rm	1050 Rm	550
Recommended											○	○	○	○	○	○	○	○

HIGH PERFORMANCE SOLID CARBIDE END MILLS 6 FLUTE EXTRA LONG LENGTH

GMG14 PLAIN SHANK
GMG15 FLAT SHANK


- The unique geometry of the variable pitch provides the best chatter free tool for high speed and trochoidal milling
- Excellent performance for Stainless Steels, Mild Steels, Cast Iron, Low/Medium hardness materials under HRC40



Unit : mm

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	D1	D2	L1	L2
GMG14060	GMG15060	6.0	6	24	75
GMG14080	GMG15080	8.0	8	32	75
GMG14100	GMG15100	10.0	10	40	100
GMG14120	GMG15120	12.0	12	48	120
GMG14160	GMG15160	16.0	16	64	140
GMG14200	GMG15200	20.0	20	80	150
GMG14250	GMG15250	25.0	25	100	170

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5 * Shank Dia. ≥ Ø12: h6



◎ : Excellent ○ : Good


ISO	P										M				K						
Material Description	Non-alloy steel					Low alloy steel				High alloy steel, and tool steel		Stainless steel			Grey cast iron		Nodular cast iron		Malleable cast iron		
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	
HRC		13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25		21	
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230	
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	
ISO	N										S						H				
Material Description	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)			Non Metallic Materials		Heat Resistant Super Alloys					Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron	
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRC											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommended											○	○	○	○	○	○	○				

HIGH PERFORMANCE SOLID CARBIDE END MILLS 6 FLUTE EXTRA LONG LENGTH CHIP SPLITTER

NEW
GMH56 PLAIN SHANK
GMH57 FLAT SHANK

Launching Jan of 2020


- Special chip splitter design for better chip removal shortened chip length at high axial machining
- High Performance for Steels, Stainless Steels and Cast Iron



Unit : mm

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length
PLAIN	FLAT	D1	D2	L1	L2
GMH56060	GMH57060	6.0	6	24	75
GMH56080	GMH57080	8.0	8	32	75
GMH56100	GMH57100	10.0	10	40	100
GMH56120	GMH57120	12.0	12	48	120
GMH56160	GMH57160	16.0	16	64	140
GMH56200	GMH57200	20.0	20	80	150
GMH56250	GMH57250	25.0	25	100	170

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5 * Shank Dia. ≥ Ø12: h6



◎ : Excellent ○ : Good

ISO	P										M				K								
Material Description	Non-alloy steel					Low alloy steel				High alloy steel, and tool steel		Stainless steel			Grey cast iron		Nodular cast iron		Malleable cast iron				
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20			
HRC		13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25		21			
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230			
Recommended	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎	◎			
ISO	N										S						H						
Material Description	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)			Non Metallic Materials		Heat Resistant Super Alloys					Titanium Alloys		Hardened steel		Chilled Cast Iron		Hardened Cast Iron	
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41		
HRC											15	30	25	38	34			55	60	42	55		
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550		
Recommended											○	○	○	○	○	○	○						

HIGH PERFORMANCE SOLID CARBIDE END MILLS 5 FLUTE LONG LENGTH

EMB72 PLAIN SHANK
EMB73 FLAT SHANK


- Special flute geometry eliminates vibrations
- Designed for mild steels, stainless steels, cast iron, tool steels, titanium alloys, prehardened steels and low hardness materials under HRC40
- Excellent finished work piece
- Higher speeds, deeper cuts and excellent metal removal rates



Unit : mm

EDP No.		Mill Diameter	Shank Diameter	Length of Cut	Overall Length	Chamfer
PLAIN	FLAT	D1	D2	L1	L2	
EMB72060	EMB73060	6.0	6	13	57	0.1
EMB72080	EMB73080	8.0	8	19	63	0.1
EMB72100	EMB73100	10.0	10	22	72	0.1
EMB72120	EMB73120	12.0	12	26	83	0.1
EMB72140	EMB73140	14.0	14	26	83	0.2
EMB72160	EMB73160	16.0	16	32	92	0.2
EMB72180	EMB73180	18.0	18	32	92	0.2
EMB72200	EMB73200	20.0	20	38	104	0.2
EMB72250	EMB73250	25.0	25	38	104	0.2

Mill Dia. Tolerance (mm)	Shank Dia. Tolerance
0 ~ - 0.03	h5 * Shank Dia. ≥ Ø12: h6



◎ : Excellent ○ : Good

ISO	P										M				K						
Material Description	Non-alloy steel					Low alloy steel				High alloy steel, and tool steel		Stainless steel				Grey cast iron		Nodular cast iron		Malleable cast iron	
VDI 3323	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	
HRC		13	25	28	32	10	29	32	38	15	35	15	23	10	10	26	3	25		21	
HB	125	190	250	270	300	180	275	300	350	200	325	200	240	180	180	260	160	250	130	230	
Recommended	◎	◎	○	○	○	◎	○	○	○	◎	○	◎	◎	◎	○	○	○	○	○	○	

ISO	N										S						H				
Material Description	Aluminum-wrought alloy		Aluminum-cast, alloyed			Copper and Copper Alloys (Bronze / Brass)			Non Metallic Materials		Heat Resistant Super Alloys				Titanium Alloys		Hardened steel	Chilled Cast Iron	Hardened Cast Iron		
VDI 3323	21	22	23	24	25	26	27	28	29	30	31	32	33	34	35	36	37	38	39	40	41
HRC											15	30	25	38	34			55	60	42	55
HB	60	100	75	90	130	110	90	100			200	280	250	350	320	400 Rm	1050 Rm	550	630	400	550
Recommended											○	○	○	○	○	◎	◎				


RECOMMENDED CUTTING CONDITIONS

GMG55, GMG56 SERIES

4 FLUTE BALL NOSE

Vc = m/min. fz = mm/tooth
RPM = rev./min. FEED = mm/min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)										
						3.0	4.0	5.0	6.0	8.0	10.0	12.0	16.0	18.0	20.0	25.0
P	1-4	Non-alloy steel	0.5D	1.0D	Vc	162	162	162	162	162	162	162	162	162	162	162
					fz	0.025	0.027	0.03	0.04	0.06	0.065	0.07	0.075	0.08	0.09	0.099
					RPM	17189	12892	10313	8594	6446	5157	4297	3223	2865	2578	2063
	5	Low alloy steel	0.5D	1.0D	FEED	1719	1392	1238	1375	1547	1341	1203	967	917	928	817
					Vc	113	113	113	113	113	113	113	113	113	113	113
					fz	0.025	0.027	0.03	0.04	0.06	0.065	0.07	0.074	0.079	0.09	0.099
					RPM	11990	8992	7194	5995	4496	3597	2997	2248	1998	1798	1439
	6-7	Low alloy steel	0.5D	1.0D	FEED	1199	971	863	959	1079	935	839	665	631	647	570
					Vc	162	162	162	162	162	162	162	162	162	162	162
					fz	0.025	0.027	0.03	0.04	0.06	0.065	0.07	0.075	0.08	0.09	0.099
	8-9	Low alloy steel	0.5D	1.0D	RPM	17189	12892	10313	8594	6446	5157	4297	3223	2865	2578	2063
					FEED	1719	1392	1238	1375	1547	1341	1203	967	917	928	817
	10-11.1	High alloyed steel, and tool steel	0.5D	1.0D	Vc	113	113	113	113	113	113	113	113	113	113	113
					fz	0.025	0.027	0.03	0.04	0.06	0.065	0.07	0.074	0.079	0.09	0.099
					RPM	11990	8992	7194	5995	4496	3597	2997	2248	1998	1798	1439
M	12-13	Stainless steel	0.5D	1.0D	FEED	1199	971	863	959	1079	935	839	665	631	647	570
					Vc	68	68	68	68	68	68	68	68	68	68	68
					fz	0.017	0.019	0.021	0.028	0.042	0.045	0.049	0.052	0.056	0.063	0.07
	14.1	Stainless steel	0.5D	1.0D	RPM	7215	5411	4329	3608	2706	2165	1804	1353	1203	1082	866
					FEED	491	411	364	404	455	390	354	281	269	273	242
					Vc	77	77	77	77	77	77	77	77	77	77	77
	14.2	Stainless steel	0.5D	1.0D	fz	0.015	0.015	0.025	0.03	0.04	0.045	0.05	0.054	0.059	0.058	0.059
					RPM	8170	6127	4902	4085	3064	2451	2042	1532	1362	1225	980
					FEED	490	368	490	490	490	441	408	331	321	284	231
K	15-20	Grey cast iron	0.5D	1.0D	Vc	85	85	85	85	85	85	85	85	85	85	85
					fz	0.02	0.02	0.025	0.041	0.045	0.05	0.055	0.06	0.064	0.065	0.068
					RPM	9019	6764	5411	4509	3382	2706	2255	1691	1503	1353	1082
	31-35	Heat Resistant Super Alloys	0.2D	0.3D	FEED	722	541	541	740	609	541	496	406	385	352	294
					Vc	77	77	77	77	77	77	77	77	77	77	77
					fz	0.02	0.02	0.025	0.041	0.045	0.05	0.055	0.06	0.064	0.065	0.068
S	36-37	Titanium Alloys	0.5D	0.3D	RPM	8170	6127	4902	4085	3064	2451	2042	1532	1362	1225	980
					FEED	654	490	490	670	551	490	449	368	349	319	267
					Vc	119	119	119	119	119	119	119	119	119	119	119
	31-35	Heat Resistant Super Alloys	0.2D	0.3D	fz	0.031	0.033	0.037	0.05	0.074	0.081	0.087	0.093	0.099	0.112	0.124
					RPM	12626	9470	7576	6313	4735	3788	3157	2367	2104	1894	1515
					FEED	1566	1250	1121	1263	1402	1227	1098	881	833	848	752
H	31-35	Heat Resistant Super Alloys	0.2D	0.3D	Vc	21	21	21	21	21	21	21	21	21	21	21
					fz	0.014	0.014	0.017	0.028	0.031	0.035	0.038	0.042	0.045	0.045	0.048
					RPM	2228	1671	1337	1114	836	668	557	418	371	334	267
	36-37	Titanium Alloys	0.5D	0.3D	FEED	125	94	91	125	104	94	85	70	67	60	51
					Vc	47	47	47	47	47	47	47	47	47	47	47
					fz	0.018	0.018	0.022	0.037	0.04	0.045	0.049	0.054	0.058	0.058	0.061




GMF52, GMF54, GMF56, GMF58, GMF60, GMF62, GMF53, GMF55, GMF57, GMF59, GMF61, GMF63 SERIES

4 FLUTE - SIDE & SLOTTING


Vc = m/min.
RPM = rev./min. fz = mm/tooth
FEED = mm/min.

ISO	VDI 3323	Material Description	Ae		Ap		Parameter	Diameter (Ø)											
			Side	Slotting	Side	Slotting		3.0	4.0	5.0	6.0	8.0	10.0	12.0	14.0	16.0	18.0	20.0	25.0
P	1-4	Non-alloy steel	0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	152	152	152	152	152	168	168	168	168	168	168	168
							fz	0.005	0.008	0.011	0.016	0.027	0.038	0.047	0.049	0.053	0.059	0.065	0.064
							RPM	16128	12096	9677	8064	6048	5348	4456	3820	3342	2971	2674	2139
							FEED	323	387	426	516	653	813	838	749	709	701	695	548
	5		0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	107	107	107	107	107	117	117	117	117	117	117	117
							fz	0.005	0.008	0.011	0.016	0.027	0.038	0.047	0.049	0.053	0.059	0.065	0.064
							RPM	11353	8515	6812	5677	4257	3724	3104	2660	2328	2069	1862	1490
							FEED	227	272	300	363	460	566	583	521	493	488	484	381
	6-7	Low alloy steel	0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	152	152	152	152	152	168	168	168	168	168	168	168
							fz	0.005	0.008	0.011	0.016	0.027	0.038	0.047	0.049	0.053	0.059	0.065	0.064
							RPM	16128	12096	9677	8064	6048	5348	4456	3820	3342	2971	2674	2139
							FEED	323	387	426	516	653	813	838	749	709	701	695	548
	8-9		0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	107	107	107	107	107	117	117	117	117	117	117	117
							fz	0.005	0.008	0.011	0.016	0.027	0.038	0.047	0.049	0.053	0.059	0.065	0.064
							RPM	11353	8515	6812	5677	4257	3724	3104	2660	2328	2069	1862	1490
							FEED	227	272	300	363	460	566	583	521	493	488	484	381
	10-11.1	High alloyed steel, and tool steel	0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	64	64	64	64	64	70	70	70	70	70	70	70
							fz	0.003	0.006	0.008	0.011	0.019	0.027	0.032	0.034	0.037	0.041	0.045	0.045
							RPM	6791	5093	4074	3395	2546	2228	1857	1592	1393	1238	1114	891
							FEED	81	122	130	149	194	241	238	216	206	203	201	160
M	12-13		0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	148	148	148	148	148	148	148	148	148	148	148	148
							fz	0.004	0.006	0.009	0.013	0.022	0.034	0.039	0.042	0.045	0.05	0.055	0.055
							RPM	15703	11777	9422	7852	5889	4711	3926	3365	2944	2617	2355	1884
							FEED	251	283	339	408	518	641	612	565	530	523	518	415
	14.1	Stainless steel	0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	106	106	106	106	106	106	106	106	106	106	106	106
							fz	0.005	0.008	0.013	0.018	0.028	0.048	0.055	0.059	0.062	0.07	0.077	0.077
							RPM	11247	8435	6748	5623	4218	3374	2812	2410	2109	1874	1687	1350
							FEED	225	270	351	405	472	648	619	569	523	525	520	416
	14.2		0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	95	95	95	95	95	95	95	95	95	95	95	95
							fz	0.005	0.008	0.013	0.018	0.028	0.048	0.055	0.059	0.062	0.069	0.076	0.076
							RPM	10080	7560	6048	5040	3780	3024	2520	2160	1890	1680	1512	1210
							FEED	202	242	314	363	423	581	554	510	469	464	460	368
K	15-20	Grey cast iron	0.5D	1.0D	1.5D (1.2D)	1.0D (0.8D)	Vc	112	112	112	112	112	123	123	123	123	123	123	123
							fz	0.006	0.01	0.014	0.02	0.034	0.048	0.058	0.061	0.065	0.073	0.081	0.079
							RPM	11884	8913	7130	5942	4456	3915	3263	2797	2447	2175	1958	1566
							FEED	285	357	399	475	606	752	757	682	636	635	634	495
S	31-35	Heat Resistant Super Alloys	0.25D	1.0D	1.0D	0.5D	Vc	26	26	26	26	26	26	26	26	26	26	26	26
							fz	0.005	0.007	0.008	0.012	0.019	0.033	0.038	0.04	0.043	0.048	0.054	0.052
							RPM	2759	2069	1655	1379	1035	828	690	591	517	460	414	331
							FEED	55	58	53	66	79	109	105	95	89	88	89	69
	36-37	Titanium Alloys	0.4D	1.0D	1.0D	0.5D	Vc	58	58	58	58	58	58	58	58	58	58	58	58
							fz	0.004	0.007	0.011	0.016	0.025	0.042	0.05	0.053	0.055	0.062	0.068	0.069
							RPM	6154	4615	3692	3077	2308	1846	1538	1319	1154	1026	923	738
							FEED	98	129	162	197	231	310	308	280	254	254	251	204

*() : Short length & Neck type



Slotting



Side Cutting

GMG16, GMG18, GMG12, GMG14, GMG17, GMG19, GMG13, GMG15 SERIES

6 FLUTE - SIDE CUTTING

Vc = m/min.
RPM = rev./min. fz = mm/tooth
FEED = mm/min.


ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)						
						6.0	8.0	10.0	12.0	16.0	20.0	25.0
P	1-4	Non-alloy steel	0.05D	2.0D	Vc	300	300	300	300	300	300	300
					fz	0.068	0.116	0.144	0.173	0.202	0.225	0.232
					RPM	15915	11937	9549	7958	5968	4775	3820
					FEED	6494	8308	8251	8260	7234	6446	5317
	5		0.05D	2.0D	Vc	203	203	203	203	203	203	203
					fz	0.05	0.085	0.106	0.128	0.149	0.167	0.174
					RPM	10769	8077	6462	5385	4039	3231	2585
					FEED	3231	4119	4110	4135	3610	3237	2698
	6-7	Low alloy steel	0.05D	2.0D	Vc	300	300	300	300	300	300	300
					fz	0.068	0.116	0.144	0.173	0.202	0.225	0.232
RPM					15915	11937	9549	7958	5968	4775	3820	
FEED					6494	8308	8251	8260	7234	6446	5317	
8-9		0.05D	2.0D	Vc	203	203	203	203	203	203	203	
				fz	0.05	0.085	0.106	0.128	0.149	0.167	0.174	
				RPM	10769	8077	6462	5385	4039	3231	2585	
				FEED	3231	4119	4110	4135	3610	3237	2698	
10-11.1	High alloyed steel, and tool steel	0.05D	2.0D	Vc	100	100	100	100	100	100	100	
				fz	0.041	0.071	0.088	0.105	0.123	0.137	0.144	
				RPM	5305	3979	3183	2653	1989	1592	1273	
				FEED	1305	1695	1681	1671	1468	1308	1100	
M	12-13		0.05D	2.0D	Vc	213	213	213	213	213	213	213
					fz	0.049	0.084	0.104	0.125	0.146	0.162	0.168
	14.1		0.05D	2.0D	RPM	11300	8475	6780	5650	4238	3390	2712
					FEED	3322	4271	4231	4238	3712	3295	2734
	14.2		0.05D	2.0D	Vc	147	147	147	147	147	147	147
					fz	0.041	0.071	0.088	0.105	0.123	0.137	0.143
S	31-35	Heat Resistant Super Alloys	0.05D	2.0D	RPM	7799	5849	4679	3899	2924	2340	1872
					FEED	1918	2492	2471	2457	2158	1923	1606
	36-37	Titanium Alloys	0.05D	2.0D	Vc	134	134	134	134	134	134	134
					fz	0.041	0.071	0.088	0.105	0.123	0.137	0.142
				RPM	7109	5332	4265	3554	2666	2133	1706	
				FEED	1749	2271	2252	2239	1967	1753	1454	
	31-35	Heat Resistant Super Alloys	0.05D	2.0D	Vc	33	33	33	33	33	33	33
					fz	0.033	0.055	0.07	0.082	0.097	0.112	0.115
	36-37	Titanium Alloys	0.05D	2.0D	RPM	1751	1313	1050	875	657	525	420
					FEED	347	433	441	431	382	353	290
	31-35	Heat Resistant Super Alloys	0.05D	2.0D	Vc	116	116	116	116	116	116	116
					fz	0.033	0.055	0.07	0.083	0.097	0.113	0.117
	36-37	Titanium Alloys	0.05D	2.0D	RPM	6154	4615	3692	3077	2308	1846	1477
					FEED	1218	1523	1551	1532	1343	1252	1037

GMH58, GMH59, GMH56, GMH57 SERIES

6 FLUTE CHIP SPLITTER - SIDE CUTTING

Vc = m/min. fz = mm/tooth
RPM = rev./min. FEED = mm/min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)						
						6.0	8.0	10.0	12.0	16.0	20.0	25.0
P	1-4	Non-alloy steel	0.05D	3.0D	Vc	270	270	270	270	270	270	270
					fz	0.034	0.058	0.072	0.087	0.101	0.113	0.116
					RPM	14324	10743	8594	7162	5371	4297	3438
					FEED	2922	3739	3713	3717	3255	2901	2393
	5	Low alloy steel	0.05D	3.0D	Vc	182.7	182.7	182.7	182.7	182.7	182.7	182.7
					fz	0.025	0.043	0.053	0.064	0.075	0.084	0.087
					RPM	9693	7269	5816	4846	3635	2908	2326
					FEED	1454	1854	1849	1861	1625	1457	1214
	6-7	Low alloy steel	0.05D	3.0D	Vc	270	270	270	270	270	270	270
					fz	0.034	0.058	0.072	0.087	0.101	0.113	0.116
					RPM	14324	10743	8594	7162	5371	4297	3438
					FEED	6494	8308	8251	8260	7234	6446	5317
	8-9	Low alloy steel	0.05D	3.0D	Vc	182.7	182.7	182.7	182.7	182.7	182.7	182.7
					fz	0.025	0.043	0.053	0.064	0.075	0.084	0.087
					RPM	9693	7269	5816	4846	3635	2908	2326
					FEED	1454	1854	1849	1861	1625	1457	1214
	10-11.1	High alloyed steel, and tool steel	0.05D	3.0D	Vc	90	90	90	90	90	90	90
					fz	0.021	0.036	0.044	0.053	0.062	0.069	0.072
					RPM	4775	3581	2865	2387	1790	1432	1146
					FEED	587	763	756	752	661	589	495
M	12-13	Stainless steel	0.05D	3.0D	Vc	191.7	191.7	191.7	191.7	191.7	191.7	191.7
					fz	0.025	0.042	0.052	0.063	0.073	0.081	0.084
					RPM	10170	7628	6102	5085	3814	3051	2441
					FEED	1495	1922	1904	1907	1670	1483	1230
	14.1	Stainless steel	0.05D	3.0D	Vc	132.3	132.3	132.3	132.3	132.3	132.3	132.3
					fz	0.021	0.036	0.044	0.053	0.062	0.069	0.072
					RPM	7019	5264	4211	3509	2632	2106	1684
					FEED	863	1121	1112	1105	971	865	723
	14.2	Stainless steel	0.05D	3.0D	Vc	120.6	120.6	120.6	120.6	120.6	120.6	120.6
					fz	0.021	0.036	0.044	0.053	0.062	0.069	0.071
					RPM	6398	4799	3839	3199	2399	1919	1536
					FEED	787	1022	1013	1008	885	789	654
S	31-35	Heat Resistant Super Alloys	0.05D	3.0D	Vc	29.7	29.7	29.7	29.7	29.7	29.7	29.7
					fz	0.017	0.028	0.035	0.041	0.049	0.056	0.058
					RPM	1576	1182	945	788	591	473	378
	36-37	Titanium Alloys	0.05D	3.0D	FEED	156	195	199	194	172	159	130
					Vc	104.4	104.4	104.4	104.4	104.4	104.4	104.4
					fz	0.017	0.028	0.035	0.042	0.049	0.057	0.059
					RPM	5539	4154	3323	2769	2077	1662	1329
					FEED	548	685	698	690	604	563	467



EMB72, EMB73 SERIES

5 FLUTE - SIDE CUTTING

Vc = m/min. fz = mm/tooth
RPM = rev./min. FEED = mm/min.

ISO	VDI 3323	Material Description	Ae	Ap	Parameter	Diameter (Ø)						
						6.0	8.0	10.0	12.0	14.0	16.0	20.0
P	1-2	Non-alloy steel	0.25D	1.25D	Vc	135	135	135	135	135	135	135
					fz	0.034	0.038	0.050	0.063	0.069	0.076	0.089
					RPM	7162	5371	4297	3581	3069	2686	2149
					FEED	1218	1021	1074	1128	1059	1021	956
	6	Low alloy steel	0.25D	1.25D	Vc	135	135	135	135	135	135	135
					fz	0.034	0.038	0.050	0.063	0.069	0.076	0.089
					RPM	7162	5371	4297	3581	3069	2686	2149
					FEED	1218	1021	1074	1128	1059	1021	956
	10	High alloyed steel, and tool steel	0.25D	1.25D	Vc	135	135	135	135	135	135	135
					fz	0.034	0.038	0.050	0.063	0.069	0.076	0.089
					RPM	7162	5371	4297	3581	3069	2686	2149
					FEED	1218	1021	1074	1128	1059	1021	956
M	12-13	Stainless steel	0.25D	1.25D	Vc	105	105	105	145	105	105	105
					fz	0.030	0.032	0.038	0.043	0.064	0.068	0.076
					RPM	5570	4178	3342	3846	2387	2089	1671
					FEED	836	668	635	827	764	710	635
	14.1	Stainless steel	0.25D	1.25D	Vc	115	115	115	115	115	115	115
					fz	0.030	0.032	0.038	0.063	0.065	0.069	0.076
K	15-20	Grey cast iron	0.25D	1.25D	RPM	6101	4576	3661	3050	2615	2288	1830
					FEED	915	732	696	961	850	789	696
					Vc	135	135	135	135	135	135	135
					fz	0.034	0.038	0.050	0.063	0.069	0.076	0.089
					RPM	7162	5371	4297	3581	3069	2686	2149
					FEED	1218	1021	1074	1128	1059	1021	956
S	31-35	Heat Resistant Super Alloys	0.25D	1.0D	Vc	25	25	25	25	25	25	25
					fz	0.017	0.020	0.025	0.036	0.045	0.048	0.060
					RPM	1326	995	796	663	568	497	398
					FEED	113	99	99	119	128	119	119
	36-37	Titanium Alloys	0.25D	1.25D	Vc	85	85	85	85	85	85	85
					fz	0.030	0.031	0.038	0.050	0.057	0.063	0.075
					RPM	4509	3382	2706	2255	1933	1691	1353
					FEED	676	524	514	564	551	533	507

